

## Product: xirodur® S180

### General Properties:

density:	1.41 g/cm <sup>3</sup>
colour:	black
saturation with moisture absorption at 23°C / 50% r. h.:	0.2 weight %
saturation with water:	0.9 weight %

### Mechanical Properties:

flexural modulus:	2700 MPa
flexural strength:	64 MPa
Shore D hardness:	78

### Thermal Properties:

highest long term service temperature:	100°C
highest short term service temperature:	120°C
lowest service temperature:	-40°C

### Electrical Properties:

specific volume resistivity:	>10 <sup>13</sup> Ωcm
surface resistivity:	>10 <sup>13</sup> Ω

The information on this Product Data Sheet is based on our current knowledge of the specified product. None of the information comprises one or more guarantees on certain properties.