

Product: iglidur® W360

General Properties:

density:	1.34 g/cm ³
colour:	yellow
saturation with moisture absorption at 23°C / 50% r. h.:	0.2 weight %
saturation with water:	1.6 weight %

Mechanical Properties:

flexural modulus:	3829 MPa
flexural strength:	119 MPa
max. permissible surface pressure at 20 °C:	75 MPa
Shore D hardness:	80

Thermal Properties:

highest long term service temperature ¹⁾ :	180°C
highest short term service temperature ^{1), 2)} :	200°C
highest short term ambient temperature ^{1), 2)} :	220°C
lowest service temperature:	-40°C

Electrical Properties:

specific volume resistivity:	>10 ¹³ Ωcm
surface resistivity:	>10 ¹² Ω

¹⁾ relaxation possible

²⁾ without additional load; no movement

The information on this Product Data Sheet is based on our current knowledge of the specified product. None of the information comprises one or more guarantees on certain properties.