

Product: iglidur® D

General Properties:

density:	1.40 g/cm ³
colour:	green
saturation with moisture absorption at 23°C / 50% r. h.:	0.3 weight %
saturation with water:	1.1 weight %

Mechanical Properties:

flexural modulus:	2000 MPa
flexural strength:	72 MPa
max. permissible surface pressure at 20 °C:	23 MPa
Shore D hardness:	78

Thermal Properties:

highest long term service temperature ¹⁾ :	90°C
highest short term service temperature ^{1), 2)} :	110°C
highest short term ambient temperature ^{1), 2)} :	140°C
lowest service temperature:	-50°C

Electrical Properties:

specific volume resistivity:	>10 ¹⁴ Ωcm
surface resistivity:	>10 ¹⁴ Ω

¹⁾ relaxation possible

²⁾ without additional load; no movement

The information on this Product Data Sheet is based on our current knowledge of the specified product. None of the information comprises one or more guarantees on certain properties.