

## Product: xirodur® F182

### General Properties:

density:	1.42 g/cm <sup>3</sup>
colour:	black
saturation with moisture absorption at 23°C / 50% r. h.:	0.2 weight %
saturation with water:	0.7 weight %

### Mechanical Properties:

flexural modulus:	3000 MPa
flexural strength:	95 MPa
Shore D hardness:	79

### Thermal Properties:

highest long term service temperature <sup>1)</sup> :	100°C
highest short term service temperature <sup>1), 2)</sup> :	120°C
lowest service temperature:	-40°C

### Electrical Properties:

specific volume resistivity:	10 <sup>6</sup> Ωcm
surface resistivity:	10 <sup>5</sup> Ω

<sup>1)</sup> relaxation possible

<sup>2)</sup> without additional load; no movement

The information on this Product Data Sheet is based on our current knowledge of the specified product. None of the information comprises one or more guarantees on certain properties.